

PRODUCT DATA SHEET

Sika® Backer Rod Fire

BACKING MATERIAL FOR FIRE RESISTANT JOINT SEALING

DESCRIPTION

Sika® Backer Rod Fire is a workable, mineral wool based backing material wrapped with a glass-fibre yarn.

USES

Sika® Backer Rod Fire is designed for fire resistant joint sealing in horizontal and vertical building structures.

CHARACTERISTICS / ADVANTAGES

- Easy to apply
- Adapts irregularities of joints
- Low water uptake

APPROVALS / STANDARDS

- Tested acc. EN 1366-4 in combination with SikaHyflex®-250 Fa cade
- Classified acc. EN 13501-2 in combination with SikaHyflex®-250 Fa cade

PRODUCT INFORMATION

Chemical Base	Mineral fiber wool wrapped with glass fiber yarn.										
Packaging	Box with 1 roll of 20 m										
Appearance / Colour	Round profile supplied in rolls										
Shelf Life	Sika® Backer Rod Fire has a shelf life of 36 months from the date of production, if it is stored in undamaged, original, sealed packaging, and if the storage conditions are met.										
Storage Conditions	Sika® Backer Rod Fire shall be stored in dry conditions, where it is protected from direct sunlight and at temperatures between +5 °C and +25 °C.										
Density	250 kg/m ³ approx. (EN 1602)										
Dimensions	For joint dimensioning see En 13501-2 classification report. In order to select the correct diameter of Sika® Backer Rod Fire the following table shall be respected: <table border="1" data-bbox="603 1624 1422 1778"> <thead> <tr> <th>Joint width</th> <th>Diameter Sika® Backer Rod Fire</th> </tr> </thead> <tbody> <tr> <td>10–12 mm</td> <td>15 mm</td> </tr> <tr> <td>12–15 mm</td> <td>20 mm</td> </tr> <tr> <td>15–25 mm</td> <td>30 mm</td> </tr> <tr> <td>25–35 mm</td> <td>40 mm</td> </tr> </tbody> </table>	Joint width	Diameter Sika® Backer Rod Fire	10–12 mm	15 mm	12–15 mm	20 mm	15–25 mm	30 mm	25–35 mm	40 mm
Joint width	Diameter Sika® Backer Rod Fire										
10–12 mm	15 mm										
12–15 mm	20 mm										
15–25 mm	30 mm										
25–35 mm	40 mm										

TECHNICAL INFORMATION

Reaction to Fire	A1	(EN 13501-1)
-------------------------	----	--------------

APPLICATION INSTRUCTIONS

APPLICATION METHOD / TOOLS

Sika® Backer Rod Fire shall be pushed into the joint with a blunt tool. To achieve maximum fire resistance between two pieces of Sika® Backer Rod Fire and in corners, Sika® Backer Rod Fire must be tightly fitted in the joint. Once Sika® Backer Rod Fire is in place, the remaining joint gap has to be sealed with SikaHyflex®-250 Facade. For information regarding joint dimensions see EN 13501-2 assessment report.

FURTHER DOCUMENTS

- EN 13501-2 classification report (in combination with SikaHyflex®-250 Facade)
- Brochure Sika Fire Protection Solutions

LIMITATIONS

- Sika® Backer Rod Fire shall be used in combination with SikaHyflex®-250 Facade.
- Limitations regarding dimensions and configuration described in the EN 13501-2 classification report must be respected.
- Sika® Backer Rod Fire shall be used by professional applicators only.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

ECOLOGY, HEALTH AND SAFETY

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in this product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0.1 % (w/w)

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

PT. SIKA INDONESIA

Jl. Raya Cibinong-Bekasi km. 20.
Cileungsi, Bogor 16820 - Indonesia
Telp. +62 21 8230025
Fax. +62 21 8230026
Website: idn.sika.com
email: sikacare@id.sika.com



PRODUCT DATA SHEET
Sika® Backer Rod Fire
August 2017
ID Nr: 02051603000000032