

PRODUCT DATA SHEET

SikaLatex[®]

BONDING AGENT

DESCRIPTION

A synthetic rubber emulsion for addition to cement mortars where good adhesion and water resistance are required.

USES

SikaLatex is a high quality emulsion which substantially increases the qualities of cement mortars, such as :

- Thin layer patching mortars
- Rendering
- Floor screeds.
- Concrete repair mortars.
- Abrasion resistant linings.
- Tile fixing mortars.
- Masonry mortars.
- Bonding agent between old and new concrete.

CHARACTERISTICS / ADVANTAGES

SikaLatex is simply added to the mixing water to provide the following beneficial properties :

- Excellent adhesion
- Reduced shrinkage.
- Greater elasticity.
- Excellent water resistance.
- Increased abrasion resistance.
- Improved chemical resistance.
- Non-toxic.

Notes: SikaLatex does not re-emulsify, even in highly alkaline conditions

PRODUCT INFORMATION

Chemical Base	Styrene Butadiene Liquid
Packaging	20 kg can 200 kg drum
Appearance / Colour	Liquid / White
Shelf Life	1 years if stored in in unopened original container.
Storage Conditions	Store in dry, cool and shaded place
Density	~1.01 kg/L

APPLICATION INFORMATION

Mixing Ratio	Added to the mixing water within the range 1 : 1 – 1 : 4 depending on application
---------------------	---

		Latex : Water							
		1 : 1		1 : 2		1 : 3		1 : 4	
Cement : sand	W/C Ratio	0.5	0.8	0.5	0.8	0.5	0.8	0.5	0.8
	1 : 1	2.3	3.0	1.5	2.1	1.1	1.5	0.9	1.2
	1 : 2	1.4	1.9	0.9	1.3	0.7	1.0	0.6	0.8
	1 : 3	1.1	1.5	0.7	1.0	0.5	0.8	0.4	0.6

Consumption of SikaLatex in kg/m² per cm thickness

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

Concrete surfaces should be clean, sound and free from oil, grease, cement laitance and all loosely adhering particles. Absorbent surfaces should be saturated thoroughly. Aggregates should be well-graded and thoroughly washed. Sand particle sizes should correspond to thickness of mortar to be applied and required surface finish.

<u>Thickness</u>	<u>Sand Size</u>
5 – 15 mm	0 – 3.0 mm
Over 15 mm	0 – 7.0 mm

APPLICATION

For all applications a bonding coat of SikaLatex – water 1 : 1 mixed with cement and/or sand should be brushed into the prepared surface.

Subsequent mortar application must be carried out whilst the bonding coat is still wet.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

PT. Sika Indonesia
Jl. Raya Cibinong-Bekasi km.20.
 Cileungsi, Bogor 16820 - Indonesia
 Tel. +62 21 8230025
 Fax. +62 21 8230026
 Website: idn.sika.com
 email: sikacare@id.sika.com



PRODUCT DATA SHEET
 SikaLatex®
 August 2016
 020301010010000001

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.