

# PRODUCT DATA SHEET

## Sika® TileFix-150

### TILE ADHESIVE

#### DESCRIPTION

Sika® TileFix-150 is a one component, pre-packed polymer modified tile adhesive mortar combining cement with selected grades of sand and several admixtures, to prevent tiles from popping up or loose. It has good adhesion.

#### USES

For bonding of ceramic, homogeneous tile, marble, granite, mosaic, and natural stone, over a range of applications as below:

- Floor and wall\*

- Interior and exterior
- Dry and wet area (not submerged)
- \* For wall application which size of tile larger than 30 x 30 cm, use Sika® TileFix-200 TA or Sika® TileFix-250 Extra.

#### CHARACTERISTICS / ADVANTAGES

- Good adhesion
- Suitable for tile with different thickness and rough back surface.
- Factory mixed – consistent quality.
- Easy to use and apply, just add water.
- Tile can be adjusted up to 20 minutes after application.

#### PRODUCT INFORMATION

Packaging	25 kg bag
Appearance / Colour	Powder / Grey
Shelf life	9 months from date of production if stored properly in original, unopened and undamaged sealed packaging
Storage conditions	Store in dry conditions at temperatures between +5 °C and +30 °C.
Density	~1.6 kg/L

#### TECHNICAL INFORMATION

Tensile Adhesion Strength	28 days	~1.0 N/mm <sup>2</sup>
---------------------------	---------	------------------------

#### APPLICATION INFORMATION

Mixing Ratio	Water : Sika® TileFix-150	6.00 L : 25 kg (by weight)
	Water : Sika® TileFix-150	1 : 3 (by volume)

<b>Consumption</b>	<p><b>For floor and wall application:</b>  ~3.8 kg per m<sup>2</sup> (based on 3 mm thickness)*  ~6.4 m<sup>2</sup> per 25 kg bag (based on 3 mm thickness)*</p> <p><b>Only for floor application:</b>  ~19.3 kg per m<sup>2</sup> (based on 15 mm thickness)*  ~1.2 m<sup>2</sup> per 25 kg bag (based on 15 mm thickness)*  *depend on substrate surface</p>
<b>Layer Thickness</b>	3 – 15 mm
<b>Ambient Air Temperature</b>	8 °C to 40 °C
<b>Pot Life</b>	~1 h (at +30 °C)
<b>Open Time</b>	~15 min (at 25 °C 75% r.H.) (depend on type of substrate)
<b>Adjustability Time</b>	~20 min (depend on type of substrate)
<b>Applied Product Ready for Use</b>	<p><b>Waiting Time Before Grouting</b>  For Wall – after 8 h  For Floor – after 24 h</p>

## APPLICATION INSTRUCTIONS

### SUBSTRATE QUALITY / PRE-TREATMENT

Concrete / screed / plaster surface must be clean, sound, level and uncontaminated by oil or grease. Remove cement laitance, dust, and loosely adhering particles.

Absorbent substrates must be pre-wetted to saturated surface dry (SSD) conditions.

### APPLICATION

- Pour 6.00 litre of water into mixing vessel then add Sika® TileFix-150 slowly and mix properly.
- Mixing time is ~ 3 minutes. A slow speed mixer is recommended (300 – 600 rpm).
- Apply with notched trowel then fix the tile. Proceed to apply while the adhesive is still wet. Size of notched depending on size of tile.
- Waiting time before grouting application minimum 24 hours. To get the best result use Sika® Tile Grout.

### LIMITATIONS

- For vertical application, it is necessary to conduct application test of ceramic which size larger than 20 x 20 cm or certain type of ceramic.
- No need to immerse the tile prior to apply.

## BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

### LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data and uses.

### ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### **PT. Sika Indonesia**

**Jl. Raya Cibinong-Bekasi km.20.**

Cileungsi, Bogor 16820 - Indonesia

Tel. +62 21 8230025

Fax. +62 21 8230026

Website: [idn.sika.com](http://idn.sika.com)

email: [sikacare@id.sika.com](mailto:sikacare@id.sika.com)



SikaTileFix-150\_en\_ID\_(12-2017)\_2\_1.pdf

Product Data Sheet

Sika® TileFix-150

December 2017, Version 02.01

020404020010000236