

PRODUCT DATA SHEET

Sikalastic®-680

SINGLE COMPONENT HIGHLY ELASTIC POLYURETHANE WATERPROOFING MEMBRANE

PRODUCT DESCRIPTION

Sikalastic®-680 is a single component, liquid applied polyurethane waterproofing membrane for concrete structures that will be covered by protective toppings. Sikalastic®-680 is flexible and provides a continuous seamless waterproofing membrane for a wide range of applications.

USES

- As waterproofing membrane on roofs, podiums, balconies, bathrooms, pools, tanks and planters
- As waterproofing coat for external wall, basements and foundations
- As water barrier under plasters, screeds or tiles

CHARACTERISTICS / ADVANTAGES

- Excellent adhesion on concrete, render and masonry
- High crack bridging ability
- Good impact and abrasion resistance
- Good chemical resistance
- Non-toxic
- Easy to use and quick drying.

PRODUCT DATA

FORM

COLOURS

Black.

PACKAGING

20 kg pail

STORAGE

STORAGE CONDITIONS / SHELF-LIFE

6 months from date of production if stored properly in undamaged and unopened original sealed packaging in cool and dry conditions. Protect from direct sunlight and frost.

TECHNICAL DATA**CHEMICAL BASE**

Polyurethane modified tar

SOLID CONTENT

~ 90%

DENSITY

Approx. 1.55 kg/litre

VOC DATA

VOC content (ready to use) not exceeding 250 gm/litre [Type of regulated paint under the Air Pollution Control (volatile organic compounds) Regulation of Hong Kong: (Roof coatings (non-exposed))].

**MECHANICAL /
PHYSICAL PROPERTIES****TENSILE STRENGTH**~ 2 N/mm²

(ASTM D 412)

ELONGATION AT BREAK

> 500 %

(ASTM D 412)

TEAR STRENGTH~ 10 N/mm²

(ASTM D 624)

ADHESIVE TO CONCRETE (AFTER 7 DAYS)~ 1.2 N/mm²**SHORE A HARDNESS**

40

(ASTM D 2240)

TACK FREE

Approx. 3 hours

(@25°C & RH 60%)

System Information**APPLICATION DETAILS****CONSUMPTION / DOSAGE***Standard Coating System*Approx. 2.0kg/m² on 2 coats (for ~ 1.2 mm dry film thickness)**AMBIENT TEMPERATURE**

+5°C min / +45°C max.

SURFACE PREPARATION

All substrates must be structurally sound, stable, dry and clean (compressive strength: min. 25 N/mm² and cohesive strength: min. 1.5 N/mm²). Smooth shiny surfaces are to be roughened while uneven surface to be leveled or filled first. All surfaces should be free of sharpness, loose materials, de-bonded coatings, curing compounds, release agents, wax residues, laitance, algae and moss, oils, dust, or any other bond inhibitors.

Structurally unsound layers and surface contaminants are to be mechanically removed by abrasive blasting, blast tracking, grinding or equivalent methods. Cracks and faulty joints should be repaired.

APPLICATION INSTRUCTIONS**PRIMING**

On very absorbent surfaces, a primer coat (dilute Sikalastic® -680 with 5 % Thinner C) should be applied on the concrete surface at consumption of 0.25 kg/ m², prior to the application of waterproofing membrane.

	<p>APPLICATION</p> <p>Sikalastic®-680 can be applied by brush, roller, trowel, squeegee or airless spray directly onto the treated substrate. Apply subsequent coats at different directions to the previous coat.</p> <p>Before applying any coating, the previous coat must be touch dry. Subsequent coats should be applied within a maximum period of 24 hours. The finished membrane should be protected from damage by other trades.</p> <p>CLEANING OF TOOLS</p> <p>Clean all tools and application equipment with Thinner C immediately after use. Hardened and/or cured material can only be removed mechanically.</p>
<p>LIMITATION</p>	<ul style="list-style-type: none"> ▪ Not to be used as trafficable top coat ▪ Do not apply directly to wet and damp surface ▪ Do not thin with water or other solvents ▪ Do not apply to areas when rain is imminent ▪ Ensure adequate ventilation during application ▪ Allow 3 days (@25°C & RH 75%) drying period before flood test on treated area. For situations of low temperature or high humidity, prolonged drying time is inevitable. ▪ For damp substrate (not fully cured), a moisture barrier coat should be applied prior to the application of Sikalastic®-680. ▪ For bitumen and asphalt surface, a barrier primer should be applied
<p>VALUE BASE</p>	<p>All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.</p>
<p>LOCAL RESTRICTIONS</p>	<p>Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.</p>
<p>HEALTH AND SAFETY INFORMATION</p>	<p>Avoid breath of vapours or material contact with skin or eyes. Ensure proper ventilation during application and curing. For full information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.</p>
<p>LEGAL NOTES</p>	<p>The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations.</p>

Sika Indonesia
 Jl. Raya Cibinong-Bekasi km.20
 Limusnunggal-Cileungsi
 16820, BOGOR
 Indonesia
 idn.sika.com

Phone: +62 21 8230025
 Fax: +62 21 8230026
 Mail: sikacare@id.sika.com

Product Data Sheet
 Sikalastic®-680
 June 2015, Version 01
 (PROVISIONAL)

