

Product Data Sheet
Edition 1, 2012
Identification no.
020801040420000001
Version no. 0010
Sikafloor® -315

Sikafloor® -315

Abrasion Resistant Aliphatic Polyurethane seal coat

Product Description Sikafloor® -315 is a three and four parts, high solids, abrasion resistant, aliphatic polyurethane based textured coatings.

Uses

- Seal coat for Sikafloor epoxy floors.
- High traffic areas requiring wear resistant coatings.

Characteristics / Advantages

- High Solids
- Excellent abrasion, wear, impact resistances
- Good UV resistance, non-yellowing
- Textured surface
- Good Chemical Resistance
- Available un-pigmented (3 parts) and pigmented (4 parts)

Product Data

Form

Appearance / Colours Sikafloor® -315 is semi-gloss after final curing. Sikafloor® -315 is available either transparent or in several standard colours. Please consult us.

Packaging

Un-Pigmented Set		Pigmented Set	
Part A:	2.83 kg	Part A:	2.83 kg
Part B:	0.42 kg	Part B:	0.42 kg
Part C:	2.13 kg (filler)	Part C:	2.13 kg (filler)
		Part D:	0.62 kg (pigment pack)
Part A+B+C	5.38 kg/set	Part A+B+C+D	6.0 kg/set

Storage

Storage Conditions / Shelf-Life 12 months from date of production if stored properly in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5°C and +30°C.

Technical Data

Chemical Base PUR

Density Part A: ~ 1.14 kg/l Part C: ~ 4.0 kg/l
Part B: ~ 0.99 kg/l Part D: ~ 2.0 kg/l

Mixed Resin: ~ 1.6 kg/l (all 4 components)

All Density values at +23°C

Mechanical / Physical Properties

Abrasion Resistance 10-20 mg (CS 17/1000/1000) After 28 days, at 23°C/50%r.h. (ASTM D 4060)

Tensile Strength 19.8 MPa After 28 days, at 23°C/50% r.h. (ASTM D2370)

Hardness 2H - 3H After 28 days, at 23°C/50% r.h. (ASTM D3363 Pencil)

Dry Film Thickness 0.09 mm DFT @ 0.1 mm WFT

VOC (g/L) 114 g/l (ASTM D2369-07)

Chemical Resistance Resistant to many chemicals. Please ask for a detailed chemical resistance table.




Table of Contents

System

Information

System Structure

Sealing of smooth EP coatings and Sikafloor® 263SL HC Décor
Base coat: e.g. Sikafloor®-263 SL HC /-264 coating (Please consult data sheets)
Sikafloor®-263 SL HC Décor (Please consult data sheet)
Matt seal coat: 1 x Sikafloor®-315

Application Details

Consumption / Dosage

Coating System	Product	Consumption
Sealing of smooth surfaces	Sikafloor®-315	~ 0.08 liter (= 0.128 kg) per m ² of DFT of approx. 0.08 mm

These figures are theoretical and do not allow for any additional material due to surface porosity, surface profile, variations in level and wastage etc.

Lower consumption can cause roller marks, gloss differences and irregular surface structure, higher consumption result in water retention.

Substrate Quality

The Sikafloor Epoxy coating shall be applied onto a concrete substrate that must be clean, dry and free of all contaminants such as dirt, oil, grease, coatings and surface treatments, etc. Pull-off strength must be not less than 1.5 N/mm². If in doubt, apply a test area first. (please consult related Sikafloor range product data sheets for details on required substrate quality).

The Sikafloor epoxy coating shall be cured and perfectly clean, sound and dry prior application of Sikafloor®- 315.

Substrate Preparation

All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by brush and/or vacuum.

Prior application of Sikafloor®- 325 onto epoxy substrate, it is recommend to roughness slightly the surface with light abrasive pads (i.e Scotch-Brite pads) and then remove all loose adhering particles.

Application Conditions / Limitations

Substrate Temperature

+15°C min. / +30°C max.

Ambient Temperature

+15°C min. / +30°C max.

Relative Air Humidity

30% min. - 75% max.

During curing the humidity should not exceed 75 % max. Adequate fresh air ventilation must be provided to remove the excess moisture from the curing product.

Dew Point

Beware of condensation!

The substrate and uncured floor must be at least 3°C above the dew point to reduce the risk of condensation or blooming on the floor finish.

Application Instructions

Mixing

Part A : part B: Part C: Part D = 100 : 15 : 75 : 22 (by weight)

Mixing Time

Do not mix more material than can be applied within the working time limits at the actual site temperature.

Empty completely the Part A, into a clean mixing container large enough to accommodate the whole set.

Then with a Jiffy mix paddle and drill, add the Part B.

Mix at low speed for 1 minute.

Then, if pigmented version is required, add the part D.

Mix for further 2 minutes.

Finally, add slowly (don't dump!) the part C (filler for textured surface) while mixing to avoid clumping. Mix for 2 minutes.

To ensure thorough mixing pour materials into another container and mix again to achieve a consistent mix.

Over mixing must be avoided to minimise air entrainment.

Mixing Tools

Sikafloor®-315 must be thoroughly mixed using a electric stirrer or other suitable equipment.

Application Method / Tools

Prior to application, confirm relative air humidity and dew point.

The Floor should be divided into section sections that can be completed without stopping.

Section should be divided at expansion joints or doorways when possible. The End of the section should be taped off to form a straight line providing a clean edge for an adjacent section.

Sikafloor®- 315 must be applied with a 3/8" (1cm) nap roller. The roller should be wet in the roller tray or bucket and the excess coating is removed by lightly rolling the tray or bucket screen so as to avoid drips.

Then apply 3 pairs of 2.5-3 m long paths on to the floor.

Then spread the material with roller passes perpendicular to the paths of the coating.

The material may be rolled to even the thickness which needs to be in the 0.08 to 0.09 mm WFT range in order to achieve proper appearance, texture, and colour development.

If applied to thick, the material may blister, if too thin, the coating will appear very flat in sheen.

It is also important to remix material often with the roller in the tray to keep filler from settling.

Cross roll the entire area with straight uninterrupted passes across the entire width of the floor. This will reduce roller marks and make the colour even. If appearance is still not uniform after a few passes, repeat this procedure.

Cleaning of Tools

Clean all tools and application equipment with Sika Thinner C immediately after use.

Hardened and/or cured material can only be removed mechanically.

Waiting Time / Overcoating

Before applying Sikafloor®-315 on Sikafloor®-263 SL HC/ 263 SL HC Décor allow:

Substrate temperature	Minimum	Maximum
+10°C	30 hours	4 days
+20°C	24 hours	3 days
+30°C	16 hours	2 days

Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.

Notes on Application / Limitations

Freshly applied Sikafloor®-315 must be protected from damp, condensation and water for at least 24 hours (+20°C).

Unevenness of substrates as well as inclusions of dirt cannot be covered by thin sealers coats. Therefore substrate and adjacent areas must be cleaned thoroughly prior to application.

Do not use on exterior, on-grade substrates Do not thin this product. Addition of thinners will slow the cure and reduce the ultimate properties of this product.

Tools

Electric drill, mixing-blade, brushes and short piled rollers 10 up to 70 cm for surface area – amount depending on size of floor). Roller frames and telescopic extension handles, tape and spatula. Plastic sheeting for placement of wet rollers.

Recommended supplier of tools:

TECHNO-Werkzeuge A.E; Vertriebs GmbH

Dieselstr. 44; 42579 Heiligenhaus, Phone: 02056 / 9846-0

Info@Techno-Vertrieb.de; Homepage: <http://www.techno-vertrieb.de>

PPW-Polyplan-Werkzeuge GmbH, Phone: +49 40/5597260, www.polyplan.com.

If heating is required do not use gas, oil, paraffin or other fossil fuel heaters, these produce large quantities of both CO₂ and H₂O water vapour, which may adversely affect the finish. For heating use only electric powered warm air blower systems.

Curing Details

Applied Product ready for use

Temperature	Foot traffic	Light traffic	Full cure
+10°C	~ 30 hours	~ 48 hours	~ 6 days
+23°C	~ 5-6 hours	~ 24 hours	~ 5-7 days
+30°C	~ 12 hours	~ 18 hours	~ 3 days

Note: Times are approximate and will be affected by changing ambient conditions

Cleaning / Maintenance

Methods

To maintain the appearance of the floor after application, Sikafloor®-304 W must have all spillages removed immediately and be regularly cleaned.

Please refer to the Sika Cleaning Regime.

Value Base

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

Local Restrictions

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

Health and Safety Information

For information and advice on the safe handling, storage and disposal of chemical products, users should refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the product when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



PT. Sika Indonesia
 Jl. Raya Cibinong- Bekasi km. 20
 Limusnunggal- Cileungsi
 BOGOR 16820 - Indonesia
 Tel. +62 21 8230025
 Fax +62 21 8230026
 Website : idn.sika.com
 e-mail: sikacare@id.sika.com

Branches
 Gresik :
 Jln. KIG Raya Utara Kav 3/4, Kawasan Industri Gresik, Roomo,
 Manyar Gresik - 61151
 Tel : 031-3951633; Fax : 031-3991632
 Medan :
 Jl. Serbaguna (Simp. Jalan Veteran), Kompleks Pergudangan Brayon
 Trade Center No. 34, Medan 20239
 Tel : (061) 844 6697, 844 6997 ; Fax : (061) 844 6698

