

PRODUCT DATA SHEET

Sika AnchorFix[®]-1

FAST CURING ANCHORING ADHESIVE

DESCRIPTION

Solvent and styrene free based, two-component polyester anchoring adhesive.

USES

Sika AnchorFix[®]-1 may only be used by experienced professionals.

As a fast curing anchoring adhesive for all grades of:

- Rebars / reinforcing steel
- Threaded rods
- Bolts and special fastening systems
- Concrete
- Hollow and solid masonry
- Hard natural stone*
- Solid rock*

* These substrates may vary greatly, in particular with regard to strength, composition and porosity. Therefore, for each application the suitability of Sika AnchorFix[®]-1 Adhesive must be tested by first applying Sika AnchorFix[®]-1 Adhesive only to a sample area. Check in particular bond strength, surface staining and discoloration.

CHARACTERISTICS / ADVANTAGES

- Fast curing
- Standard guns can be used
- Can be used at low temperatures
- High load capacity
- ETA Approval available
- Non-sag, even overhead
- Styrene-free
- Low odour
- Low wastage

APPROVALS / STANDARDS

- Injection system for use in masonry according to ETAG 029, ETA-12/0227, Declaration of Performance 020403010010000001 5034408, certified by notified product certification body 0679, certificate of constancy of performance 0679-DPD-0777, and provided with the CE marking
- Bonded injection type anchor for non cracked concrete according to ETAG 001 annex 1 and 5, ETA-13/0720, Declaration of Performance 020403010010000001 5034408, certified by notified product certification body 1020, certificate of constancy of performance 1020-CPD-090-029816, and provided with the CE marking.

PRODUCT INFORMATION

Packaging	150 ml standard cartridge	20 cartridges per box pallet: 75 boxes
	300 ml standard cartridge	12 cartridges per box pallet: 75 boxes
	550 ml standard cartridge	12 cartridges per box pallet: 50 boxes
Colour	Component A:	white
	Component B:	black
	Component A+B mixed:	light grey
	Stone colour:	
	Component A:	white
	Component B:	salmon
Component A+B mixed:	beige	
Shelf life	12 months from date of production All Sika AnchorFix®-1 cartridges have the expiry date printed on the label.	
Storage conditions	Stored properly in original, unopened, sealed and undamaged packaging in dry conditions at temperatures between +5 °C and +25 °C. Protect from direct sunlight.	
Density	~1.63 kg/L (component A+B mixed)	

TECHNICAL INFORMATION

Compressive Strength	~60 N/mm ² (7 days, +20 °C)	(ASTM D 695)
Modulus of Elasticity in Compression	~3 500 N/mm ² (7 days, +20 °C)	(ASTM D 695)
Tensile Strength in Flexure	~28 N/mm ² (7 days, +20 °C)	(ASTM D 790)
Tensile Strength	~12 N/mm ² (7 days, +20 °C)	(ASTM D 638)
Modulus of Elasticity in Tension	~4 500 N/mm ² (7 days, +20 °C)	(ASTM D 638)
Thermal Resistance	Long term	+50 °C
	Short term (1–2 hours)	+80 °C
Glass Transition Temperature	+60 °C	(DIN EN ISO 6721-1)
Design Considerations	For details about adhesive anchoring design refer to the separate documentation provided: "Technical Documentation Sika AnchorFix®-1" Ref: 870 43 01	

APPLICATION INFORMATION

Mixing ratio	Component A : component B = 10 : 1 by volume
Layer Thickness	3 mm max.
Sag Flow	Non-sag, even overhead
Product Temperature	Sika AnchorFix®-1 must be at a temperature of between +5 °C and +40 °C for application.
Ambient Air Temperature	-10 °C min. / +40 °C max.
Dew Point	Beware of condensation. Substrate temperature during application must be at least 3 °C above dew point.
Substrate Temperature	-10 °C min. / +40 °C max.

Curing time

Temperature	Open time - T _{gel}	Curing time - T _{cur}
+30 °C	4 minutes	35 minutes
+25 °C – +30 °C	4 minutes	40 minutes
+20 °C – +25 °C	5 minutes	50 minutes
+10 °C – +20 °C	6 minutes	85 minutes
+5 °C – +10 °C	10 minutes	145 minutes
+5 °C	18 minutes	145 minutes
-10 °C ^{1 2}	30 minutes	24 hours

1 Minimum cartridge temperature: +5 °C

2 This application is not covered by the scope of the product ETA or any other approval.


APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY


- Mortar and concrete must be at the required strength. No need to be 28 days old.
- Substrate strength (concrete, masonry, natural stone) must be verified.
- Pull-out tests must be carried out if the substrate strength is unknown.
- The anchor hole must always be clean, dry, free from oil and grease etc.
- Loose particles must be removed from the holes.
- Threaded rods and rebars have to be cleaned thoroughly from any oil, grease or any other substances and particles such as dirt etc.

MIXING


Getting the cartridge ready: 300 ml / 550 ml




1. Unscrew the cap



2. Cut the film



3. Screw on the static mixer




4. Place the cartridge into the gun and start application


When the work is interrupted the static mixer can remain on the cartridge after the gun pressure has been relieved. If the resin has hardened in the nozzle when work is resumed, a new nozzle must be attached.

APPLICATION METHOD / TOOLS


Anchors in solid masonry / concrete




Drilling of hole with an electric drill to the diameter and depth required. Drill hole diameter must be in accordance with anchor size.



The drill hole must be cleaned with a blow pump or by compressed air, starting from the bottom of the hole. (at least 2x)
Important: use oil-free compressors.




The drill hole must be cleaned with a blow pump or by compressed air, starting from the bottom of the hole. (at least 2x)
Important: use oil-free compressors.




Pump approx. twice until both parts come out uniformly. Do not use this material. Release the gun pressure and clean the cartridge opening with a cloth.




The drill hole must be thoroughly cleaned with the special steel brush (brush at least 2x). The diameter of the brush must be larger than the diameter of the drill hole.



Inject the adhesive into the hole, starting from the bottom, while slowly drawing back the static mixer. In any case avoid entrapping air. For deep holes extension tubing can be used.




The drill hole must be cleaned with a blow pump or by compressed air, starting from the bottom of the hole. (at least 2x)
Important: use oil-free compressors.



Insert the anchor with a rotary motion into the filled drill hole. Some adhesive must come out of the hole.
Important: the anchor must be placed within the open time.




The drill hole must be thoroughly cleaned with the special steel brush (brush at least 2x). The diameter of the brush must be larger than the diameter of the drill hole.




During the resin hardening time the anchor must not be moved or loaded. Wash tools immediately with Sika® Colma Cleaner. Wash hands and skin thoroughly with warm soap water.


Anchors in hollow blocks




Drilling of hole with an electric drill to the diameter and depth required. Drill hole diameter must be in accordance with anchor and perforated sleeve size.
Note: with hollow material do not use rotary hammer drills.




The drill hole must be thoroughly cleaned with a round brush (brush at least 1x). The diameter of the brush must be larger than the diameter of the drill hole.




The drill hole must be cleaned after each cleaning step with a blow pump or by compressed air, starting from the bottom of the hole (pump at least 1x).
Important: use oil-free compressors.




Insert perforated sleeve completely into the drill hole.




Pump approx. twice until both parts come out uniformly. Do not use this material. Release the gun pressure and clean the cartridge opening with a cloth.




Inject the adhesive into the perforated sleeve, starting from the bottom, while slowly drawing back the static mixer. In any case avoid entrapping air.



Close the cap from the perforated sleeve to avoid some escape of the resin during entering the steel rod.



Insert the anchor with a rotary motion into the filled perforated sleeve. Use the adequate steel rod size.
Important: the anchor must be placed within the open time.



During the resin hardening time the anchor must not be moved or loaded. Wash tools immediately with Sika® Colma Cleaner. Wash hands and skin thoroughly with warm soap water.

CLEANING OF TOOLS

Clean tools and application equipment with Sika® Colma Cleaner immediately after use. Hardened / cured material can only be mechanically removed.

FURTHER DOCUMENTS

For design details, please refer to the separate documentation provided:

Technical Documentation Sika AnchorFix®-1 Ref: 870 43 01

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

PT. Sika Indonesia

Jl. Raya Cibinong-Bekasi km.20.

Cileungsi, Bogor 16820 - Indonesia

Tel. +62 21 8230025

Fax. +62 21 8230026

Website: idn.sika.com

email: sikacare@id.sika.com



PRODUCT DATA SHEET
Sika AnchorFix®-1
December 2016
020205010010000001